

# LJ Collection

## Larson-Juhl Artique Specification

### Complete Board

- High-quality alpha cellulose, lignin-free.
- Pigments are used which are fade and bleed resistant. On the Blue Wool Scale it measures a reading of 5 minimum.
- Water-soluble extracts are minimal i.e. chloride below 0.05%, sulphate below 0.25%.
- Buffered with calcium carbonate.\*
- Passes the Silver Tarnish Test and Photographic Activity Test.

\* *Minimum 3-5% by weight*

### The adhesive

- Neutral pH buffered with calcium carbonate\*, thus eliminating the issue of acids forming within the adhesive layers.
- Is plasticiser-free.

### Accelerated ageing test

TAPPI T.509 SU68

Years

Unaged - pH8.9

100 -pH8.9

200 -pH8.9

300 -pH8.9

Larson-Juhl Artique fully complies to FATG Conservation level