



Timecare®

SolidCore Board

SolidCore

Complete Board

- Made from high-quality, bleached alpha cellulose in 1, 2, 3, or 4 ply, each being the same. The board is lignin-free.
- Only natural pigments are used which are fade and bleed resistant. On the Blue Wool Scale it measures a reading of 5 minimum.
- Water-soluble extracts are minimal i.e. chloride below 0.05%, sulphate below 0.25%.
- Buffered with calcium carbonate.*
- Passes the Silver Tarnish Test and Photographic Activity Test making it suitable for mounting precious photographs.

**Minimum 3-5% in weight*

The adhesive

- Neutral pH buffered with calcium carbonate*, thus eliminating the issue of acids forming within the adhesive layers.
- Is plasticiser-free.

Accelerated ageing test

TAPPI T.509 SU68

Unaged -- pH 9.4

100 years – pH 7.5

150 years – pH 7.5

200 years - pH 7.5

SolidCore fully complies to FATG Conservation level